



□ - BASF

We create chemistry

SLENTEX® 210/1

Technical Data Sheet

SLENTEX® 210/1

Technical Data Sheet

DESCRIPTION

SLENTEX® 210/1 is a high performance aerogel insulation material. SLENTEX® 210/1 is supplied in blanket form and has a slim form factor that easily conforms to various shapes, geometries, and configurations. SLENTEX® 210/1 is vapour permeable, hydrophobic, has excellent fire performance properties, and is suitable for use across a wide temperature range.

The desired performance and suitability for use at any service temperature must be tested and qualified by the end user.

PRODUCT DIMENSIONS

Form	Rolls
Length	6.1 m / 20 ft
Thickness	10 mm / 0.4 in
Width	150 cm / 59 in
Density	12 - 15 lb/ft³

FLAMMABILITY PROPERTIES

CAN/ULC S102	Class A - Flame Spread 0 Smoke Developed 5
ASTM E84	Class A - Flame Spread 0 Smoke Developed 0
CAN/ULC-S114, Determination of non-combustibility in building materials	Non-Combustible

For more information on this product, please contact the BASF Tech Desk at 800.527.8324 or techquestions.na@basf.com

IMPORTANT! The information, data and products presented herein are based upon information reasonably available to BASF at the time of publication, and are presented in good faith, but are not to be construed as guarantees or warranties, express or implied, regarding performance, results to be obtained from use comprehensiveness merchantability, or that said information, data or products can be used without infringing patents of third parties. You should thoroughly test any application, and independently determine satisfactory performance before commercialization.



We create chemistry

SLENTEX® 210/1

Technical Data Sheet

PHYSICAL PROPERTIES

Compressive strength at 10% strain, ASTM C165-07	15 kPa / 313 psf
Compressive strength at 25% strain, ASTM C165-07	91 kPa / 1901 psf
Linear shrinkage under soaking heat at 650 deg C, ASTM 356-17	(L,W,H) 1.07%, 0.83%, 4.79%, 5.23% mass change
Maximum use temperature, ASTM C447-15	650 °C
Water vapor sorption, ASTM C1104	2.76 wt.% (0.6 v%)
Corrosion using leached solution, ASTM C1617-15	Non-Corrosive
Water absorption by immersion, ASTM C1763	3.99 wt.%

THERMAL PROPERTIES

R value (Hr. ft ² F / BTU inch)	7.9
--	-----

R Value Table

Temp (°C)	R Value (Hr. ft ² F / BTU inch)
-150	10.6
-100	9.1
0	7.5
24	7.9
100	6.3
200	5.3
300	4.1
400	3.1
500	2.4
600	1.7

For more information on this product, please contact the BASF Tech Desk at 800.527.8324 or techquestions.na@basf.com

IMPORTANT! The information, data and products presented herein are based upon information reasonably available to BASF at the time of publication, and are presented in good faith, but are not to be construed as guarantees or warranties, express or implied, regarding performance, results to be obtained from use comprehensiveness merchantability, or that said information, data or products can be used without infringing patents of third parties. You should thoroughly test any application, and independently determine satisfactory performance before commercialization.



We create chemistry

SLENTEX® 210/1

Technical Data Sheet

STORAGE RECOMMENDATIONS

- Store in a dry area, protected against direct sunlight
- Avoid contact with organic solvents

SAFETY AND HANDLING RECOMMENDATIONS

- For information regarding safe product handling, consult the product Safety Data Sheet.
- For sever emergencies contact CHEMTREC at 1-800-424-9300 or the BASF HOTLINE: 1-800-832-HELP (4357)

For more information on this product, please contact the BASF Tech Desk at 800.527.8324 or techquestions.na@basf.com

IMPORTANT! The information, data and products presented herein are based upon information reasonably available to BASF at the time of publication, and are presented in good faith, but are not to be construed as guarantees or warranties, express or implied, regarding performance, results to be obtained from use comprehensiveness merchantability, or that said information, data or products can be used without infringing patents of third parties. You should thoroughly test any application, and independently determine satisfactory performance before commercialization.



We create chemistry